



# INSULATION TAPE PE

Flexibele polyethyleentape voor gebruik in verwarming en sanitair

|                                  |                       |                                                                                        |
|----------------------------------|-----------------------|----------------------------------------------------------------------------------------|
| <b>DRAGER</b>                    | Polyethyleenschuim    |                                                                                        |
| <b>DIKTE</b>                     | 3 mm                  |                                                                                        |
| <b>BREEDTE</b>                   | 50 mm                 |                                                                                        |
| <b>LENGTE</b>                    | 10 m                  |                                                                                        |
| <b>KLEUR</b>                     | Grijs                 |                                                                                        |
| <b>SAMENSTELLING VAN DE LIJM</b> | Acrylaatdispersie     |                                                                                        |
| <b>LINER</b>                     | Bruin siliconenpapier |                                                                                        |
| <b>AFSCHILWEERSTAND</b>          | DIN EN 1939           | Materiaalbreuk                                                                         |
| <b>GEBRUIKSTEMPERATUUR</b>       | EN 14707              | -30 °C tot +100 °C                                                                     |
| <b>TREKSTERKTE</b>               | ISO 1926              | In de lengterichting: 290 kPa<br>In de dwarsrichting: 180 kPa                          |
| <b>REK BIJ BREUK</b>             | ISO 1926              | In de lengterichting: 130 %<br>In de dwarsrichting: 95 %                               |
| <b>DRUKSTERKTE</b>               | ISO 3386-1            | 110 kPa bij 50 % compressie                                                            |
| <b>COMPRESSIESET</b>             | ISO 1856-C            | 25 % (22 uur bij 23 °C)<br>21 % (0,5 uur na ontlasting)<br>10 % (24 uur na ontlasting) |
| <b>WATERABSORPTIE</b>            | ISO 2896              | < 1 Vol. - % (7d)                                                                      |



NMC reserves the right to update the product line or its technical features to the state-of-the-art technology anytime and without previous announcement. All given information is to the best of our knowledge. If you have any questions concerning technical details please contact the NMC information service. Any partial reproduction or reprint shall require our explicit approval.

08/2026 responsible publisher:  
NMC sa · Gert-Noël-Strasse · B-4731 Eynatten

#### NMC sa

Gert-Noël-Strasse · B-4731 Eynatten

Phone: +32 87 85 85 00 · Fax: +32 87 85 83 55

E-Mail: [info@nmc.eu](mailto:info@nmc.eu)

[www.nmc-insulation.com](http://www.nmc-insulation.com)

